

Appl. No. 10/711,035
Amdt. dated July 17, 2006
Reply to Office action of June 19, 2006

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

- 5 1.(original) A repairing method for a liquid crystal display panel comprising:
- continuously providing a first pressure to two opposite surfaces of the liquid crystal display panel;
- continuously providing a second pressure to two opposite surfaces of
10 the liquid crystal display panel, and removing a sealant in a liquid crystal injection area;
- continuously providing a third pressure to two opposite surfaces of the liquid crystal display panel to press liquid crystal out through the liquid crystal injection area, and cleaning the pressed-out liquid
15 crystal;
- sealing the liquid crystal injection area with a fresh sealant and continuously providing a fourth pressure to two opposite surfaces of the liquid crystal display panel; and
- curing the fresh sealant and removing the fourth pressure.
20
- 2.(original) The repairing method of claim 1, wherein the liquid crystal injection area is a liquid crystal injection hole.
- 3.(original) The repairing method of claim 2 , further comprising removing
25 the sealant outside the liquid crystal injection hole before providing the first pressure.

Appl. No. 10/711,035
Amdt. dated July 17, 2006
Reply to Office action of June 19, 2006

4.(original) The repairing method of claim 1 wherein the liquid crystal injection area is a portion of a sealing area of the liquid crystal display panel, and an auxiliary structure is formed at an edge of the liquid crystal display panel beside the portion of the sealing area.

5

5.(original) The repairing method of claim 4 wherein the auxiliary structure is formed by filling a gap of the liquid crystal display panel with an ultraviolet sensitive material and curing the ultraviolet sensitive material.

10

6.(original) The repairing method of claim 4 wherein the liquid crystal display panel is filled up with the liquid crystal utilizing a one-drop-fill method.

15 7.(original) The repairing method of claim 1 used for repairing an uneven defect on the liquid crystal display panel caused by a gravity issue.

8.(original) The repairing method of claim 1 wherein the step of removing the sealant in the liquid crystal injection area utilizes a laser to burn down the sealant.

20

9.(original) The repairing method of claim 1 wherein temperature of the liquid crystal display panel is maintained at 20 to 80°C when providing the first pressure.

25

10.(original) The repairing method of claim 1 wherein temperature of the liquid crystal display panel is maintained at 20 to 80°C when providing the second pressure.

Appl. No. 10/711,035
Amdt. dated July 17, 2006
Reply to Office action of June 19, 2006

11.(original) The repairing method of claim 1 wherein temperature of the liquid crystal display panel is maintained at 20 to 80°C when providing the third pressure.

5

12.(original) The repairing method of claim 1 wherein the first pressure equals the second pressure.

13.(original) The repairing method of claim 1 wherein the second pressure equals the third pressure.

10

14.(withdrawn) The repairing method of claim 1 wherein the third pressure is larger than the fourth pressure, the fourth pressure is larger than the first pressure, and the first pressure is similar to the second pressure.

15